

## WHEN SUBMITTING MASONRY SAMPLES FOR JAHN COLOR SELECTION, PLEASE PAY ATTENTION TO THE FOLLOWING:

- 1. TAKE SAMPLE(S):** Select locations that represent typical color and texture.  
Send one sample for each color needed.  
*Color:* **SEND A CLEANED SAMPLE, IF BUILDING WILL BE CLEANED.  
The lab will not clean any samples.**  
*Texture:* Send a tooled sample if patch will be tooled.  
Sample size: No smaller than 2" x 2" - larger if possible (**No Powder!**)
- 2. MARK SAMPLE(S):** The surface to be matched must be clearly indicated.
- 3. COMPLETE SAMPLE INFORMATION FORM:** Project Manager or Architect must complete the attached form and return it. One form should be completed for each sample being sent. **We cannot begin to process your samples until we receive the form(s) and payment.**
- 4. SEND SAMPLE(S) AND FORM TO:** Cathedral Stone Products, Inc.  
7266 Park Circle Drive  
Hanover, MD 21076  
Fax: (410) 782-9155

### *Allow 2 Weeks for Processing Jahn Color Samples*

You Will Receive: • One hard sample

- One matching dry powder sample

The dry powder should be mixed and applied on site (from the same location that sample was removed) as a color mock-up.

Directions for mixing, application, and curing are included or can be found on [www.cathedralstone.com](http://www.cathedralstone.com).

*(The site-applied sample should match our finished laboratory sample)*

If necessary we will notify you if we determine that a Standard or Custom Jahn color matches your masonry sample.

*Please note the following exceptions:*

**Terra Cotta –** We will supply your choice of Standard color or custom match the surface color. In either case, the Jahn repair should be painted with CSP's terra cotta glazing system to prevent water intrusion.

**Granite –** It is not possible for us to match the multicolored appearance of granite. We will supply you with a suitable matching background color – the appropriate aggregate (granite dust, etc.) must be added on site to the surface of the damp Jahn mortar. It may be necessary to lightly wash the finished repair with a mild acetic acid (white vinegar) to expose the aggregate within one or two days.

**Marble –** The Jahn M120 Marble Repair Mortar will be supplied in a uniform color. If attempting to simulate veining, on site techniques must be developed, possibly using paint, stains or a darker Jahn mix applied in veins carved into the Jahn repair.